

Technical Information



Solumer™ 875L

Polyolefin Elastomer

Introduction

Solumer™ 875L is an ethylene-octene copolymer produced via Nexlene™ technology. It performs well in a wide range of general purpose thermoplastic elastomer applications and has excellent flow characteristics

Applications

- General purpose thermoplastic elastomers
- Wire and cable

- Impact modification
- Footwear

Properties

| | - 1 | | Typical Values | Unit | Test Method |
|-------------------------|-----------------------------------|-----------------|----------------|---------------------|------------------------|
| Physical | Density | | 0.868 | g/cm ³ | ASTM D792 |
| Properties | Melt index (2.16 kg @190°C) | | 5.0 | g/10min | ASTM D1238 |
| | Mooney viscosity (ML1+4 @ 121°C) | | 8 | MU | ASTM D1646 |
| Mechanical | Tensile strength at break | | 63 | kgf/cm ² | ASTM D638 ² |
| Properties ¹ | Elongation at break | | >1,000 | % | ASTM D638 ² |
| | Tensile modulus (100% Elongation) | | 24 | kgf/cm ² | ASTM D638 ² |
| | Flexural modulus (1% secant) | | 110 | kgf/cm ² | ASTM D790 |
| | Tear strength (Type C) | | 38 | kgf/cm ² | ASTM D624 |
| | Hardness | Shore A (1 sec) | 66 | | ASTM D2240 |
| | | Shore D (1 sec) | 17 | | ASTM D2240 |
| Thermal Properties | Melting temperature | | 62 | °C | SK Method |
| | Glass transition temperature | | -52 | °C | SK Method |

¹ Evaluated using compression molded sample, process condition: 170 °C, 4 min

Notes

These are typical values and are not to be construed as specifications. The physical properties are highly dependent on the manufacturing conditions. So customers should confirm performances by their own tests.

For additional sales, order and technical assistance

Head office SK geo centric Co.,LTD 51 Jong-ro, Jongno-gu, Seoul, Republic of Korea TEL +82-2-2121-7067

TS&D SK innovation Institute of Environmental Science & Technology, 325 Exporo, Yueseong-gu,

Daejeon, Republic of Korea TEL +82-42-609-8871

² Crosshead speed: 500 mm/min.