

# Texin<sup>®</sup> 770A

## Characterization

Texin 770A resin is an aromatic polyether-based thermoplastic polyurethane; it can be processed by injection molding or extrusion.

## Properties / Applications

Texin 770A resin is characterized by very good hydrolysis resistance, good low temperature flexibility, resiliency and impact strength, high moisture vapor transmission rates and is plasticizer free. Texin 770A natural color resin complies with FDA food-contact regulations 21 CFR 177.1680 (Polyurethane Resins) and 177.2600 (Rubber Articles Intended for Repeated Use), subject to the limitations of these and any other applicable regulations. Applications include soft touch over-molding, roof linings, seals, membranes, films, rigid/flexible composite systems and sport shoe soles. As with any product, use of Texin 770A resin in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

## Storage, Drying and Regrind Usage

Texin thermoplastic polyurethane resins are hygroscopic and will absorb ambient moisture. The resins should remain in their sealed containers and stored in a dry area. Storage temperatures should not exceed 86°F (30°C). Unused resin from opened containers, or reground material that is not to be used immediately, should also be stored in sealed containers under cool and dry conditions.

Prior to processing, Texin 770A resin must be thoroughly dried for a minimum of 4 hours in a pre-heated desiccant dehumidifying hopper dryer to a moisture content of less than 0.03%. Hopper inlet air temperature should be 180-200°F (82-93°C), the inlet air dew point should be -20°F (-29°C) or lower.

Where end-use requirements permit, up to 20% Texin resin regrind may be used with virgin material. Regrind material must be generated from properly molded/extruded parts, sprues, runners, trimmings, and/or films. Degraded or discolored material may not be used for regrind. All regrind material must be free of contamination and thoroughly blended with virgin material prior to drying and processing. Finish parts containing regrind must be tested to ensure that end-use requirements are fully met.

# Texin<sup>®</sup> 770A

## Injection Molding, Extrusion and Blow Molding Conditions

Typical starting conditions for injection molding, extrusion, and blow molding are noted below. Actual processing conditions will depend on machine size, mold design, material residence time, shot size, part geometry, etc.

### Typical Injection Molding Conditions

|                            |                                |
|----------------------------|--------------------------------|
| Barrel Temperature: Rear   | 360°–380°F (182°–193°C)        |
| Barrel Temperature: Middle | 370°–390°F (188°–199°C)        |
| Barrel Temperature: Front  | 370°–390°F (188°–199°C)        |
| Barrel Temperature: Nozzle | 375°–395°F (191°–202°C)        |
| Melt Temperature           | 370°–390°F (188°–199°C)        |
| Mold Temperature           | 60°–100°F (16°–38°C)           |
| Injection Pressure         | 8,000 - 13,000 psi             |
| Hold Pressure              | 60 - 80% of Injection Pressure |
| Back Pressure              | 800 psi max.                   |
| Screw Speed                | 40 - 80 rpm                    |
| Injection Speed            | Slow to Moderate               |
| Cushion                    | 1/8 in max                     |

### Extrusion and Blow Molding Profile

#### Typical Temperature Profile for Extrusion

|                     |                             |
|---------------------|-----------------------------|
| Rear (Feed)         | 360° - 390°F (182° - 199°C) |
| Middle (Transition) | 360° - 400°F (182° - 204°C) |
| Front (Meter)       | 360° - 400°F (182° - 204°C) |
| Die                 | 370° - 400°F (188° - 204°C) |
| Melt                | 375° - 400°F (191° - 204°C) |

# Texin<sup>®</sup> 770A

## Typical Properties\* for Natural Resin

| Property                                                               | ASTM Test Method<br>(Other) | Texin 770A Resin<br>U.S. Units | Texin 770A Resin<br>S.I. Units |
|------------------------------------------------------------------------|-----------------------------|--------------------------------|--------------------------------|
| <b>General</b>                                                         |                             |                                |                                |
| Specific Gravity                                                       | D 792 (ISO 1183)            | 1.07                           | 1.07                           |
| Shore Hardness                                                         | D 2240 (ISO 868)            | 70A                            | 70A                            |
| Taber Abrasion:<br>H-18, 1,000-g Load, 1,000<br>Cycles                 | D 3489 (ISO 4649)           | 7 mg Loss                      | 7 mg Loss                      |
| Bayshore Resilience                                                    | D 2632                      | 68%                            | 68%                            |
| Mold Shrinkage,<br>100-mil thickness                                   | D 955 (ISO 2577)            |                                |                                |
| Flow Direction                                                         |                             | 0.008 in/in (mm/mm)            | 0.008 in/in (mm/mm)            |
| Cross-Flow Direction                                                   |                             | 0.008 in/in (mm/mm)            | 0.008 in/in (mm/mm)            |
| <b>Mechanical</b>                                                      |                             |                                |                                |
| Tensile Strength                                                       | D 412 (ISO 37)              | 3,700 lb/in <sup>2</sup>       | 25.5 MPa                       |
| Tensile Stress at 100%<br>Elongation                                   | D 412 (ISO 37)              | 500 lb/in <sup>2</sup>         | 3.4 MPa                        |
| Tensile Stress at 300%<br>Elongation                                   | D 412 (ISO 37)              | 750 lb/in <sup>2</sup>         | 5.2 MPa                        |
| Ultimate Elongation                                                    | D 412 (ISO 37)              | 770%                           | 770%                           |
| Flexural Modulus:<br>73°F (23°C)                                       | D 790 (ISO 178)             | 2,100 lb/in <sup>2</sup>       | 14.5 MPa                       |
| -22°F (-30°C)                                                          |                             | 15,500 lb/in <sup>2</sup>      | 106.9 MPa                      |
| Tear Strength, Die C                                                   | D 624 (ISO 34)              | 345 lbf/in                     | 60.5 kN/m                      |
| Compression Set<br>(postcured): <sup>a</sup>                           | D 395-B (ISO 815)           |                                |                                |
| 22 Hours at 158°F (70°C)                                               |                             | 30%                            | 30%                            |
| 22 Hours at 73°F (23°C)                                                |                             | 11%                            | 11%                            |
| <b>Thermal</b>                                                         |                             |                                |                                |
| Glass Transition<br>Temperature (T <sub>g</sub> )                      | (DMA) <sup>b</sup>          | -71°F                          | -57°C                          |
| Vicat Softening Temperature,<br>Rate A<br>(0.125-in, 10N, 0.833°C/min) | D 1525 (ISO 306)            | 167°F                          | 75°C                           |

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

<sup>a</sup> Postcured for 16 hours at 230°F (110°C), not postcuring will result in lower values.

<sup>b</sup> DMA – Dynamic Mechanical Analysis



# Texin<sup>®</sup> 770A

## Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling this product. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., safety data sheets and product labels. For further information contact your Covestro LLC representative or the Product Safety and Regulatory Affairs Department in Pittsburgh, PA.

## Regulatory Compliance Information

Some of the end uses of the products described in this bulletin must comply with applicable regulations, such as the FDA, NSF, USDA, and CPSC. If you have any questions on the regulatory status of these products, contact your Covestro representative or Regulatory Affairs Manager in Pittsburgh, PA.

## Note

***The purchaser/user agrees that Covestro LLC reserves the right to discontinue this product without prior notice.***

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you utilize our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Editor: Covestro LLC  
1 Covestro Circle  
Pittsburgh, Pennsylvania 15205  
United States  
[www.covestro.com](http://www.covestro.com)

**Contact:**  
TPU Single Point of Contact  
e-mail: [tpuinfo@covestro.com](mailto:tpuinfo@covestro.com)